

Approval number :

Customer :

Product : HK 6 combined 1-150x70 degree street lamp lens

Material Code : 1.02.91851

PN: HK-50@09-150X70-5050-#0-0g-6

Manufacturer : Chengdu HercuLux Photoelectric Technology Co.,Ltd



	Supplier confirmation			Client confirmation			
Proposed		DATE		Qualified□		D 4 75	
Project manager		DATE		Unqualified□		DATE	
Audit		DATE		Audit		DATE	
Approved		DATE		Approved		DATE	
Stamp		DATE		Stamp		DATE	

( Confirmation of acceptance by both parties must be signed and sealed )

 Factory: Chengdu Shuangliu District, Iot industrial park 2 road HercuLux Photoelectric Park

 Phone:
 028-85887727 (801)
 028-85887990 (801)
 Fax:
 028-85887730
 http://www.herculux.cn/

 Sales Dept:
 Shenzhen Nanshan
 District Nanshan Cloud Valley Innovation Industrial Park Comprehensive Service Building,

 TEL:
 0755-2937 1541
 FAX:
 0755-2907 5140


\*Approval In duplicate, for both supplier and customer.




TEL: 0755-2937 1541	FAX: 0755-2907 5140	http://www.herculux.cn/	Date updated: 2022/1/7
Product Picture			
PN		HK-50@09-150X70-5050-#0	-0g-6
Size(L*W*H/Φ*H)		L:50mm*W:50mm*H:09m	ım
Material		РС	
Effiency:		/	
Temperature(Topr)		xtreme temperature resistance ng-term use temperature : -40°	
FWHM		/	
Matched LES		5050	

# Product 2D drawings







## Technical Requirement:

- 1. The surface don't have any defects of flash, shrink and bubble.
- 2. The uncharted fillet and pattern draft subject to the 3D drawing.
- 3. The uncharted dimensional tolerance subject to the 3D drawing.

)ptical Design			HK-50@09-150X70-5050-#0-0g-6		1.02.91851
ructure Design		HK 6 combined 1-150x70 degree street lamp lens	Pages	Qty	Weight
Assess			2		
Authorized		Material:PC		CDHK	



# Sample size test report HK 6 combined 1-150x70 degree street lamp lens

### HERCULUX <sup>恒坤光电</sup>

			Standard size	Upper Size limit		wer limit	Test result1	Test result2	Test result3	Test result4	Jud gme nt	Remarks
	width	1	50	50.1	49	. 7	49.99	49.92	49.93	49.84	OK	
	The thicknes	c of	2	2.25	1.	95	2.01	2.06	2.07	2.13	OK	Test
	The aperture		3.5	3.65	3.	35	3.55	3.53	3.56	3.51	OK	environment:
4.01	Position column		1.2	1.35	0.85		1.01	1.01	0.98	1.08	ОK	' In 20 ℃ -25 ℃
1.Size	positi colum	on n	2	2.1	1.	85	1.95	1.94	1.96	1.96	ок	environment to achieve thermal equilibrium
	diameter position column spacing		45	45.2	44	. 8	45.01	45.02	45	45	ок	after the test.
	<b>1</b>	<u> </u>		Gate she	ar ca	n not	affect the a	ppearance	of the lamp	)		
				See atta	chme	nt "Ap	opearance	Inspection	Standards"			
2.Appear	ance		See achment	E		١	No burr	No burr	No burr	No bu	rr	ок
Quality	Quality Inspect		spection andards"			N	o stains	No stains	No stains	No stai	ns	ÜK
3.Material				PC				Color	Tra	nsparent		OK
	Testing I						5050					
4.Optica		y of th		he source of the test, if it is required to be out of range. According to the heat dissipation amp and the actual conditions of the use environment, the lens should be fully tested and tested to prevent the lens life. See light distribution curve								
l index							70.5°					
	Angle	9					X153.5° (No glass)					ОК
	Effiend	су							/	/		OK
	Facula	See t	the signatu	gnature sample								
	ehensive ment							Q	ualified			
					PC	prod	luct size ch	anges wit	n temperat	ture table	2	
Caliper 2 Height G Microsco Thick Ga Gauge E 2、 Amb the size o	Number: V D-Quadra auge M-To pe P-Neeo uge R-Ra	e on	Lengti change ( mm	5 0.8		10	20	30 40	→Si →Si →Si →Si	ze: 1 ze: 1	00 տու 50 տու 00 տու 50 տու	
Precautio				the law-				wont th - 1		(°C)		amin ata -
2. Try to 3. The le gently. D MMA Boo 4. The w	avoid touc ns surface o not wipe dy, etc.). orking tem	hing t is co with	the total re- intaminated industrial s ure of the l	ens should	ace v a sof ohol, be w	vhen t t cotto isopr ithin t	taking the loon cloth dip opanol, ace he tempera	ens. ped in anal etone, ethei iture resista	ytically pure r, toluene, > ance limit of	e neutral so cylene, carl f the lens n	olvent bon te nateria	to wipe trachloride,

Exceeding the temperature resistance limit will cause the lens to crack or melt and affect the service life of the lens. It is recommended that the upper surface temperature of the LED colloid should be less than 120 degrees.


Packaging Information



P	N	HK-50@09-150X70-5050	-#0-0g-6	Product Name	combined 1-150x70 c	legree s	street lamp		
Product	material	PC		Customer					
Package diagram		Single Vacut	um package	Box	Dackage	>			
Product packing		24	A/box	4	Box/layer				
		14	Layer/the box	1344	A/the box				
	NO.	Material Code	Item name	Specification	Single box usage	Unit	Remarks		
	1	2.07.0049	Blister box	23cm*21cm	56	PCS			
<b>D</b>	2	2.08.0001	PE film	25cm*27cm	56	Block			
Packagin g Materials	3	2.06.0005	inside the	62mm*42mm	56	Piece			
water als	4	2.06.0005	inside the	62mm*70mm	1	Piece			
	4	2.06.0003	large clapboard	46cm*42cm	15	PCS			
	4	2.06.0011	large carton	48cm*44cm*37c	em 1	PCS			
Remarks	Scattered packaging is not restricted by this specification, the customer has the requirements of the customer shall prevail								

# Special notice

When gule pass through holes, columns and other structures, or part of the thin structure, will form a weld line. The product which uses multi-point injection welding line will appear because of the combination of sol, as shown below:



Please note :

The appearance of lines in the structure of the product as well as at the screw hole is a normal phenomenon, will not affect the actual use of the product, and can not be avoided at this stage.



### Appearance inspection standards

### 1 Operating procedures

1.1.1Sampling standards, sampling plan and AQL

Test level : GB/T2828.1-2012The first part is according to the acceptance quality limit (AQL) retrieval batch inspection sampling plan, general inspection level  $\Pi$  level, CR class defect coefficient 0, MA defect rejection level AQL = 0.65, MI class defect rejection level AQL = 1.0; defect level please see 5.4.

2 Code table

Code	Code description	Unit	Code	Code description	Unit
N	Amount/pcs	pcs	D	Diameter	mm
L	Length	mm	Н	Depth	mm
W	Width	mm	DS	Distance	mm
S	Proportion	mm²	SS	Offset	mm

#### 3 Test conditions

3.1 Sight distance and working hours: Sight distance should be 30-35cm, each side of the inspection time does not exceed 12s, the visual angle of 45-135 degrees;

3.2 Light: 2x40w cool white fluorescent lamp, the light source is 500-550mm away from the lens surface; in order to make the appearance defect can be correctly recognized, the illumination should be 500-1000Lux, and the observation time is 10 seconds.

3.3 Visual inspection staff should be 1.0 (including corrected visual acuity) above, no color blindness, color weakness.

#### 4 Appearance inspection standards

Test items	ludeing atop doub	Inspection equipment	Defect level		
i est items	Judging standard	Testing method	МІ	MA	CR
	When start the machine and process, all products have to check the appearance of the sample, the appearance of the sample is divided into qualified samples and limited samples.				
Check the sample	1: Qualified sample refers to the appearance and structure standard of the product which recognized by the client, the sample size should be confirmed before mass production;	tructure standard of the product which nized by the client, the sample size Sample			V
	2: The limited sample refers to the limit of a particular exceptionally developed sample. Limit the sample only for its specific point of exception to confirm; The priority is higher than the other criteria in this table. When there is a limited sample, the limit sample shall prevail.				

	1				
Raw edge	Not allowed to affect the size and assembly	Visual, point card		V	
Scratch	1: Non-optical surface and non-exposed surface scratches should be visually insignificant and the length is less than 1/10 of the maximum surface size.	Visual, point card, calipers		v	
Fingerprint	Fingerprints are not allowed on all products	Visual		V	
Foreign things, impurities	The product may not be attached to foreign objects, including oil, fiber, dregs of water gap and so on				v
Deformation	Insufficient filling shall not affect the appearance of the assembly and the exposed surfaces.	Visual, feeler			V
Poor ejection	Products may not appear bad ejection, including no convex top, thimble printed on the assembly surface shall not be higher than the product surface, non-assembled surface thimble height should not exceed the product size tolerances; thimble printing should be less than the product surface and no more than 0.3; thimble surface treatment should be consistent with the product side. Ejection strain: the optical surface and the appearance of the exposed surface after assembly are not allowed to have a strain, and the structural surface does not allow visual obvious strain.	Visual, point card		V	
Insufficient filling	Insufficient filling shall not affect the appearance of the assembly and the exposed surfaces, The signature sample shall prevail.	Visual, point card		~	
Shrink	When the entire surface of the product shrinks, the optical properties and dimensions must meet the requirements, and the visual will not significantly affect the appearance.Part shrink reference point defects	Visual, point card		V	
Flow marks、Welding	1 : Product does not allow the presence of flow marks and welding lines unless the structure can not be avoided;	Visual		~	
line	2: The remaining flow marks shall not appear in the optical surface, a single L $\leq$ 10mm, no more than two				
Bubble	No bubbles are allowed	Visual		√	
Foreign objects, black spots, white spots	Not obvious or $D \le 0.3$ mm black spots and foreign bodies in the area of 100x100mm not more than 1; Exceeded foreign matter black spots is judged bad.	Visual, point card	V		
Damaged	No damage is allowed	Visual			√
Cold glue	Optical surface may not have cold glue, non- optical surface cold glue should meet the visual is not obvious.	Visual	$\checkmark$		
	1: Do not affect the product size, shall not penetrate the optical surface, the cut should be smooth;				
Bad incision	2: Laser cutting products, the optical surface burns shall not occur after the processing is completed. Beading must not affect product installation	Visual			V
	3: Three molds and hot runner gate shall not appear residue.				
Scrub	Scrub surface should be uniform, off the scrub phenomenon should not be obvious , A single off scrub imprint requires $D \le 1 \text{ mm}$ and no more than 1 area within a 50x50 mm area	Visual		V	