**HERCULUX** Chengdu HercuLux Photoelectric 恒坤光电 Technology Co.,Ltd **Product Approval** 

Approval number :

Customer : Product : Hk-6 In 1 Lamp Lens (TNB) Material Code : 1.02.12725 PN : HK-50@09-150X50-5050-#0-1g-6 Synthetic information:1.07.81402\_HK-257@02-0221-S Manufacturer : Chengdu HercuLux Photoelectric Technology Co.,Ltd



	Supplier confirmation			Client confirmation				
Proposed		DATE		Qualified□		DATE		
Project manager		DATE		Unqualified□		DATE		
Audit		DATE		Audit		DATE		
Approved		DATE		Approved		DATE		
Stamp		DATE		Stamp		DATE		

( Confirmation of acceptance by both parties must be signed and sealed )

 Factory: Chengdu Shuangliu District, Iot industrial park 2 road HercuLux Photoelectric Park

 Phone:
 028-85887727 (801)
 028-85887990 (801)
 Fax:
 028-85887730
 <a href="http://www.herculux">http://www.herculux</a>.

 Sales Dept:
 Shenzhen Nanshan
 District Nanshan Cloud Valley Innovation Industrial Park Comprehensive Service Building,

 TEL:
 0755-2937 1541
 FAX:
 0755-2907 5140


\*Approval In duplicate, for both supplier and customer.




TEL: 0755-2937 1541	FAX: 0755-2907 5140 http://www.herculux.cn/ Date updated: 2021/9/15
Product Picture	
PN	HK-50@09-150X50-5050-#0-1g-6
Size(L*W*H/Φ*H)	L:50mm*W:50mm*H:09mm
Material	PC
Effiency:	≥88%
Temperature(Topr)	Material limit temperature resistance: -40°C to +120°C Long-term use temperature: -40°C to +90°C
FWHM	: 150°X50°
Matched LES	5050

第2页








## Technical Requirement:

- 1. The surface don't have any defects of flash, shrink and bubble.
- 2. The uncharted fillet and pattern draft subject to the 3D drawing.
- 3. The uncharted dimensional tolerance subject to the 3D drawing.

Ptical Design HK-50@09-150X50-5050-#		50-5050-#0-1g-6	1.02.12725		
ructure Design		Hk-6 In 1 Lamp Lens (TNB)	Pages	Qty	Weight
Assess			2		
Authorized		Material:PC		CDHK	



# Sample size test report Hk-6 In 1 Lamp Lens (TNB)



			Standard size	Upper Size limit	Lowe size lir	-	Test result1	Test result2	Test result3	Test result4	Jud gme nt	Remarks
	width The thickness of The aperture		50	50.15	49. ′	7	49.92	49.94	49.86	50.05	OK	
			2	2.1	1.9		2.02	2	2	2.03	ок	<b>-</b> /
			3.5	3.65	3.3		3.41	3.4	3.43	3.38	ОК	Test environment
	Positi	on	1.2	1.3	0.9		1.06	1.02	0.99	1	ОК	ln 20 ℃ -25 ℃
1.Size	<u>colum</u> positi colum diamet	on In	2	2.1	1.9		2.01	2.03	2.03	2.02	ок	environment to achieve thermal equilibrium
	positi colum spacin	on In	45	45.15	44.8	35	45	44.99	44.98	45	ок	after the test
		<u> </u>		Gate she	ar can i	not a	affect the a	ppearance	of the lamp	)		
				See atta	chment	t "Ap	pearance	Inspection	Standards"			
2.Appear	ance		See achment pearance	E		No burr		No burr	No burr	No burr		ОК
Insp		spection andards"	_		No stains		No stains	No stains	No stains		2	
3.Materia	ıl			PC	PC			Color	Tra	nsparent		ОК
	Testing	LED						5050				
	FWH	М		See light distribution curve								
4.Optica I index	Angle	e	(50)	° x150° )	$\pm 5^{\circ}$		53.4° x151.8°	$\searrow$	$\backslash$	$\overline{}$		ОК
	Effien	ency		≥88%			90%					OK
	Facula	Seet	the signatu	re sample			`				-	
-	hensive ment							Q	ualified			
		<u> </u>			PC p	rod	uct size ch	anges wit	h temperat	ture table	2	
Remarks: 1、Tool Number: V-Vernier Caliper 2D-Quadratic H-			-	Length 0.9 changes 0.8 (mm) 0.7 Size: 50mm 								
Height Gauge M-Tool Microscope P-Needle T-				0.6 0.5 0.4 Size: 150mm						50mm		
Thick Gauge R-Radius Gauge E-Visual.					0.4 -					-	.ze: 2 .ze: 2	
2、 Ambient temperature on the size of the product refer to the table on the right					0.2 - 0.1 -			-	++	_ <b>→</b> Si	ze: 3	00mm
to the tab	ble on the	nyni			0	1		1	1 1			

Precautions:

Wear clean gloves during lens assembly to prevent contamination of the lens surface.
 Take the lens try to avoid touching the total reflection surface.
 When the lens surface contamination, you can only gently wipe with soft cotton sticky neat neutral solvent, not allowed to wipe with industrial solvents.


Packaging Information



P	N	HK-50@09-150X50-5050-	-#0-1g-6	Product Name	Hk-6 In 1 Lamp	Lens (T	NB)	
Product	material	PC		Customer				
Package diagram		Single Vacut	im package	Box pa	ckage	>		
Product	packing	24	A/box	4	Box/layer			
		14	Layer/the box	1344	A/the box			
	NO.	Material Code	Item name	Specification	Single box usage	Unit	Remarks	
	1	2.07.0049	Blister box	23cm*21cm	56	PCS		
Deskesis	2	2.08.0001	PE film	25cm*27cm	56	Block		
Packagin g Materials	3	2.06.0005	inside the	62mm*42mm	56	Piece		
materials	4	2.06.0005	inside the	62mm*70mm	1	Piece		
	4	2.06.0003	large clapboard	46cm*42cm	15	PCS		
	4	2.06.0011	large carton	48cm*44cm*37cm	1	PCS		
Remarks	Scattered packaging is not restricted by this specification, the customer has the requirements of the customer shall prevail							

## Special notice

When gule pass through holes, columns and other structures, or part of the thin structure, will form a weld line. The product which uses multi-point injection welding line will appear because of the combination of sol, as shown below:



Please note :

The appearance of lines in the structure of the product as well as at the screw hole is a normal phenomenon, will not affect the actual use of the product, and can not be avoided at this stage.



### Appearance inspection standards

### 1 Operating procedures

1.1.1Sampling standards, sampling plan and AQL

Test level : GB/T2828.1-2012The first part is according to the acceptance quality limit (AQL) retrieval batch inspection sampling plan, general inspection level  $\Pi$  level, CR class defect coefficient 0, MA defect rejection level AQL = 0.65, MI class defect rejection level AQL = 1.0; defect level please see 5.4.

2 Code table

Code	Code description	Unit	Code	Code description	Unit
N	Amount/pcs	pcs	D	Diameter	mm
L	Length	mm	Н	Depth	mm
W	Width	mm	DS	Distance	mm
S	Proportion	mm²	SS	Offset	mm

#### 3 Test conditions

3.1 Sight distance and working hours: Sight distance should be 30-35cm, each side of the inspection time does not exceed 12s, the visual angle of 45-135 degrees;

3.2 Light: 2x40w cool white fluorescent lamp, the light source is 500-550mm away from the lens surface; in order to make the appearance defect can be correctly recognized, the illumination should be 500-1000Lux, and the observation time is 10 seconds.

3.3 Visual inspection staff should be 1.0 (including corrected visual acuity) above, no color blindness, color weakness.

#### 4 Appearance inspection standards

	ludeing atop doud	Inspection equipment	Defec	t level	
Test items	Judging standard	Testing method	МІ	MA	CR
	When start the machine and process, all products have to check the appearance of the sample, the appearance of the sample is divided into qualified samples and limited samples.				
Check the sample	1: Qualified sample refers to the appearance and structure standard of the product which recognized by the client, the sample size should be confirmed before mass production;	Sample comparison , visual			V
	2: The limited sample refers to the limit of a particular exceptionally developed sample. Limit the sample only for its specific point of exception to confirm; The priority is higher than the other criteria in this table. When there is a limited sample, the limit sample shall prevail.				

	Ι			1	1
Raw edge	Not allowed to affect the size and assembly	Visual, point card		$\checkmark$	
Scratch	1: Non-optical surface and non-exposed surface scratches should be visually insignificant and the length is less than 1/10 of the maximum surface size.	Visual, point card, calipers		v	
Fingerprint	Fingerprints are not allowed on all products	Visual		V	
Foreign things, impurities	The product may not be attached to foreign objects, including oil, fiber, dregs of water gap and so on				V
Deformation	Insufficient filling shall not affect the appearance of the assembly and the exposed surfaces.	Visual, feeler			V
Poor ejection	Products may not appear bad ejection, including no convex top, thimble printed on the assembly surface shall not be higher than the product surface, non-assembled surface thimble height should not exceed the product size tolerances; thimble printing should be less than the product surface and no more than 0.3; thimble surface treatment should be consistent with the product side. Ejection strain: the optical surface and the appearance of the exposed surface after assembly are not allowed to have a strain, and the structural surface does not allow visual obvious strain.	Visual, point card		V	
Insufficient filling	Insufficient filling shall not affect the appearance of the assembly and the exposed surfaces , The signature sample shall prevail.	Visual, point card		√	
Shrink	When the entire surface of the product shrinks, the optical properties and dimensions must meet the requirements, and the visual will not significantly affect the appearance.Part shrink reference point defects	Visual, point card		V	
Flow marks、Welding	1 : Product does not allow the presence of flow marks and welding lines unless the structure can not be avoided;	Visual		√	
line	2: The remaining flow marks shall not appear in the optical surface, a single L $\leq$ 10mm, no more than two				
Bubble	No bubbles are allowed	Visual		√	
Foreign objects, black spots, white spots	Not obvious or $D \le 0.3$ mm black spots and foreign bodies in the area of 100x100mm not more than 1; Exceeded foreign matter black spots is judged bad.	Visual, point card	V		
Damaged	No damage is allowed	Visual			√
Cold glue	Optical surface may not have cold glue, non- optical surface cold glue should meet the visual is not obvious.	Visual	V		
	1: Do not affect the product size, shall not penetrate the optical surface, the cut should be smooth;				
Bad incision	2: Laser cutting products, the optical surface burns shall not occur after the processing is completed. Beading must not affect product installation	Visual			v
	3: Three molds and hot runner gate shall not appear residue.				
Scrub	Scrub surface should be uniform, off the scrub phenomenon should not be obvious , A single off scrub imprint requires $D \le 1 \text{ mm}$ and no more than 1 area within a 50x50 mm area	Visual		V	