

HERCULUX Chengdu HercuLux Photoelectric Technology Co.,Ltd

Product Approval


Approval number:

Customer:

Manufacturer: Chengdu HercuLux Photoelectric Technology Co.,Ltd

| PN | Code | Product |
|---------------------------|--------------|------------------------------------|
| HK-50@05-90-3030-#0-1g-12 | 1. 02. 91741 | HK 12close1-90degree Road lam Lens |
| HK-50@05-60-3030-#0-1g-12 | 1. 02. 91748 | HK 12close1-60degree Road lam Lens |
| HK-50@06-30-3030-20-1g-12 | 1. 02. 91804 | HK 12close1-30degree Road lam Lens |







91741 91748 91804

| | Supplier o | confirmation | | | Client | confirmation | |
|--------------------|------------|--------------|--|--------------|--------|--------------|--|
| Proposed | | DATE | | Qualified□ | | | |
| Project manager | | DATE | | Unqualified□ | | DATE | |
| Audit | | DATE | | Audit | | DATE | |
| Approved | ed DATE | | | Approved | | DATE | |
| Stamp | Stamp | | | Stamp | | DATE | |

(Confirmation of acceptance by both parties must be signed and sealed)

 ${\it Factory:}\ Chengdu\ Shuangliu\ District,\ Iot\ industrial\ park\ 2\ road\ HercuLux\ Photoelectric\ Park$

Phone: 028-85887727 (801) 028-85887990 (801) Fax: 028-85887730 www.hkoptics.com
Sales Dept: Shenzhen Nanshan District Nanshan Cloud Valley Innovation Industrial Park Comprehensive Service Building, 501-505

TEL: 0755-2937 1541 FAX: 0755-2907 5140


*Approval In duplicate, for both supplier and customer.



TEL: 0755-2937 1541 FAX: 0755-2907 5140 www.hkoptics.com Date updated: 2019/7/25

| Product Picture: | |
|--------------------|--------------------------|
| PN: | HK-50@XX-X-3030-#0-1g-12 |
| Size(L*W*H/Φ*H): | L:50mm; W:50mm; H:Xmm |
| Material: | PC |
| Effiency: | \ |
| Temperature(Topr): | -40°C to +80°C |
| FWHM: | 90°,60°,30° |
| Matched LES: | 3030 |






Technical remark:


- 1. The 3D map is not indicated for rounded corners and draft angle.
- 2. The dimensional tolerances are not specified according to GB/T 14486 2008 MT5.
- 3, The surface has no flash, shrinkage, bubbles and other defects.

| | Optical | design | | | | | | HK-50@ | HK-50@05-90-3030-#0-1g-12 | | | | |
|----|---------|---------|------|----|-----|-------------|----------------------------|-----------------|------------------------------------|--|--|--|--|
| | tructur | e desig | | | | HK 12close1 | -90degree Road lam Lens | | 1.02.91741 er of drawin atv weight | | | | |
| | Rev | riew | | | | Ī | 20.13 | umber of drawin | mber of drawin qty weight | | | | |
| | اما:ما | -4: | | | | NA-Ai-I | DC | | CDUIK | | | | |
| | valid | ation | | | | Material: | PC | CDHK | | | | | |
|)~ | ~250 | 250~ | ~450 | >4 | 450 | | | | | | | | |

| MT5 | Basic size | <3 | 3∼10 | 24~65 | 65~140 | 140~250 | 250~450 | >450 | |
|------------|-----------------|------|-------|-------|--------|---------|---------|------|--|
| Tolerance | | | 0 10 | 00 | 00 1.0 | 1.0 200 | 200 .00 | | |
| | olerance valu | ±0.1 | ±0.15 | ±0.35 | ±0.50 | ±0.80 | ±1 2 | ±2.0 | |
| table (mm) |) Dierance valu | ±0.1 | ±0.15 | ±0.55 | ±0.50 | ±0.60 | ±1.2 | ±2.0 | |








Technical remark:

- 1. The 3D map is not indicated for rounded corners and draft angle.
- 2. The dimensional tolerances are not specified according to GB/T 14486 2008 MT5.
- 3, The surface has no flash, shrinkage, bubbles and other defects.

| | Optical | design | | | | | | HK-50@05-60-3030-#0-1g-12 | | | | |
|------------|---------|---------|------|----|-----|-------------|----------------------------|---------------------------|-----|--------|--|--|
| | tructur | e desig | | | | HK 12close1 | -60degree Road lam Lens | 1.02.91748 | | | | |
| | Rev | iew | | | | | | umber of drawin | qty | weight | | |
| | Valid | ation | | | | Material: | PC | CDHK | | | | |
| <u>)</u> - | ~250 | 250~ | ~450 | >4 | 450 | | | | | | | |

| MT5 Tolerance | Basic size | <3 | 3~10 | 24~65 | 65~140 | 140~250 | 250~450 | >450 | |
|------------------|---------------|------|-------|-------|--------|---------|---------|------|--|
| | olerance valu | ±0.1 | ±0.15 | ±0.35 | ±0.50 | ±0.80 | ±1.2 | ±2.0 | |






Technical remark:


- 1. The 3D map is not indicated for rounded corners and draft angle.
- 2. The dimensional tolerances are not specified according to GB/T 14486 2008 MT5.
- 3, The surface has no flash, shrinkage, bubbles and other defects.

| | Optical | design | | | | | | HK-50 | @06-30-3030-2 | 0-1g-12 |
|----|----------------|-----------------|--|--|-------------|----------------------------|----|----------------|---------------|---------|
| | tructure desig | | | | HK 12close1 | -30degree Road lam Lens | | | | |
| | | | | | | | | umber of drawi | n qty | weight |
| | i.cv | IC VV | | | | | | | | |
| | Validation | | | | | Material: | PC | | CDHK | |
| 0^ | ~250 | 50 250~450 >450 | | | | | | | | |


| MT5 Tolerance | Basic size | <3 | 3~10 | 24~65 | 65~140 | 140~250 | 250~450 | >4 | 50 | |
|------------------|---------------|------|-------|-------|--------|---------|---------|-----|----|--|
| | olerance valu | ±0.1 | ±0.15 | ±0.35 | ±0.50 | ±0.80 | ±1.2 | ±2. | .0 | |

































| | | | Standard size | Upper Size limit | Lower size limi | Test result1 | Test result2 | Test result3 | Test result4 | Jud gme nt | Remarks |
|--|--|--|-----------------------------|----------------------|----------------------------------|-----------------|-----------------|-----------------|---|------------------|--|
| | le | ength | 50 | | | 49. 9 | 49. 95 | 49. 93 | 49. 98 | \setminus | |
| | W | idth | 50 | | | 49. 93 | 49. 96 | 49. 96 | 49. 95 | | Test environment: In |
| 1.Size | | ng column acing | 45 | | | 49. 95 | 49. 96 | 49. 96 | 49. 97 | | 20 °C -25 °C environment to achieve thermal equilibrium after the |
| | Locat | ing post | 2 | | | 1.95 | 1. 95 | 1. 96 | 1. 95 | | test. |
| | thi | ckness | 2. 15 | | | 2. 13 | 2. 15 | 2. 13 | 2. 15 | | |
| | | | | Gate she | ar can no | t affect the a | ppearance | of the lamp | | | |
| | | | | See atta | chment "A | Appearance I | nspection S | Standards" | | | |
| 2.Appear | rance | See atta | | E | | No burr | No burr | No burr No burr | | | OK |
| Quality | | Inspection S | | | | No stains | No stains | No stains | No stai | ns | |
| 3.Materia | al . | | | PC Color Transparent | | | | | | | OK |
| 4.Optica | The reco | ting LED 3030 commended size and power rating of the LED light source recommended for this lens should be composed the test, if it is required to be out of range. According to the heat dissipation capability of the lamposed conditions of the use environment, the lens should be fully tested and tested to prevent the lens lens lens light distribution curve | | | | | | | mp and the actual | | |
| I index | a | ngle | | | | | | | | | |
| | K- | -value | | | | | | | | | |
| | Effi | ciency | | | | | | | | | |
| | Facula | See the sign | ature samp | ole | | ` | | | | | |
| Compre judg | ehensive ment | | | | | • | Qualified | | | | |
| 2D-Quad Tool Micr Gauge R 2、Amb | Number: \ Iratic H-He roscope P -Radius G ient tempe | /-Vernier Cal eight Gauge I -Needle T-Th Gauge E-Visu erature on the to the table | M- nick al. e size | cha | PC ngth 1 nges 0.8 0.6 0.4 0.2 0 | product size | te changes | 40 | Size: Size: Size: 100m Size: 150m CO | 50m | |
| Precautio | ons: | | | | | | | | | | |

- 1、Wear clean gloves during lens assembly to prevent contamination of the lens surface.
- Take the lens try to avoid touching the total reflection surface.
 When the lens surface contamination, you can only gently wipe with soft cotton sticky neat neutral solvent, not allowed to wipe with industrial solvents.
- 4. The working temperature of the lens should be within the temperature limit of the lens material. Exceeding the temperature limit will cause damage to the lens and affect the service life of the lens.



| | | | Standard size | Upper Size limit | Lower size limit | Test result1 | Test result2 | Test result3 | Test result4 | Jud gme nt | Remarks |
|---|---|-------------------------|----------------------------|---------------------|------------------|-------------------------------|-----------------|-----------------|-----------------|------------------|--|
| | lengt | h | 50 | | | 50. 15 | 50. 16 | 50. 12 | 50. 15 | | |
| | widt | h | 50 | | | 50. 14 | 50. 15 | 50. 13 | 50. 16 | | Test equirement la |
| 1.Size | Locati colum spacin | n | 45 | | | 44. 95 | 44. 97 | 44. 95 | 44. 96 | | Test environment: In 20 °C -25 °C environment to achieve thermal equilibrium after the |
| | Locati post | - | 2 | | | 1. 95 | 1. 97 | 1. 95 | 1. 96 | | test. |
| | thickne | ess | 2. 15 | | | 2. 18 | 2. 15 | 2. 17 | 2. 15 | | |
| | | amp | | | | | | | | | |
| | | | | | | | | | | | |
| 2.Appear | rance | | See achment pearance | nce E | | No burr | No burr | No burr | No bu | rr | ОК |
| Quality | | | spection andards" | | No stair | | No stains | No stains | No stains | | |
| 3.Materia | al | | | PC | - | | Color | Tra | nsparent | | OK |
| 4.Optica | to the so | mmer ource actual | of the test, | if it is requ | ired to be o | out of range ent, the lens | . According | to the hear | t dissipatio | n cap | uld be comparable ability of the lamp event the lens life. |
| I index | angle | | | | | | | | | | |
| | K-val | | | | | | | $\overline{}$ | $\overline{}$ | | |
| | Efficie | | | | | | | // | // | | |
| | Facula | | the signatu | re sample | | , I. | | | | | |
| | ehensive ment | | | | | • | Q | ualified | | | |
| Caliper 2 Height G Microsco Thick Ga Gauge E 2、Amb the size o | PC product size changes with temperature table Length changes (mm) O.8 Gauge M-Tool Gauge R-Radius E-Visual. Inbient temperature on the of the product refer table on the right PC product size changes with temperature table Size: 50mm O.8 O.9 O.9 O.9 O.9 O.9 O.9 O.9 | | | | | | | | | | |
| Precaution | ons: | | | | | | | | | | |

- Wear clean gloves during lens assembly to prevent contamination of the lens surface.
 Take the lens try to avoid touching the total reflection surface.
 When the lens surface contamination, you can only gently wipe with soft cotton sticky neat neutral solvent, not allowed to wipe with industrial solvents.
 The working temperature of the lens should be within the temperature limit of the lens material. Exceeding the
- temperature limit will cause damage to the lens and affect the service life of the lens.



| | | | Standard size | Upper Size limit | Lower size limit | Test result1 | Test result2 | Test result3 | Test result4 | Jud gme nt | Remarks |
|---|---|--------------------------------|----------------------------|--------------------------|------------------|-------------------------------|-----------------|-----------------|--|------------------|--|
| | lengt | h | 50 | | | 50. 18 | 50. 13 | 50. 08 | 50. 17 | | |
| | widt | h | 50 | | | 50. 19 | 50. 12 | 50. 11 | 50. 18 | | Task and incompasts to |
| 1.Size | Locati colum spacin | n | 45 | | | 44. 97 | 44. 98 | 44. 97 | 44. 95 | | Test environment: In 20 °C -25 °C environment to achieve thermal equilibrium after the |
| | Locati post | _ | 2 | | | 1. 91 | 1.9 | 1. 91 | 1.9 | | test. |
| | thickne | ess | 5. 95 | | | 6. 05 | 6 | 6.06 | 6. 05 | | |
| | | • | | Gate | shear can | not affect th | ne appearar | nce of the la | amp | | |
| | | | | See | attachmen | t "Appearar | ice Inspecti | on Standar | ds" | | |
| 2.Appear | rance | | See achment bearance | | | No burr | No burr | No burr | No burr | | OK |
| Quality | | Ins | spection andards" | | | lo stains | No stains | No stains | No stai | ns | |
| 3.Materia | al | | | PC | | | Color | Tra | nsparent | | OK |
| 4.Optica | to the so | mmer ource actual | of the test, | if it is requ | ired to be | out of range ent, the lens | . According | to the hear | t dissipatio | n cap | uld be comparable ability of the lamp event the lens life. |
| I index | angle | | | | | | | | | | |
| | K-val | ue | | | | | | // | / | | |
| | Efficie | | | | | | | | | | |
| | Facula | See t | he signatu | re sample | | ` | | | | | |
| | ehensive ment | | | | | | Qı | ualified | | | |
| Juag | | | | | PC pro | duct size o | hanges wi | th temper | ature tab | le | |
| Caliper 2 Height G Microsco Thick Ga Gauge E 2、Amb the size o | Number: \ D-Quadra auge M-Tope P-Needuge R-Ra | tic H- ool dle T- dius erature | e on | Length change (mm | 5 | 10 2 | 0 30 | * - | Size: 50 Size: 100mm Size: 150mm Size: 200mm | 0mm | |
| Precautio | ons: | | | | | | | | | | |

- Wear clean gloves during lens assembly to prevent contamination of the lens surface.
 Take the lens try to avoid touching the total reflection surface.
 When the lens surface contamination, you can only gently wipe with soft cotton sticky neat neutral solvent, not allowed to wipe with industrial solvents.
 The working temperature of the lens should be within the temperature limit of the lens material. Exceeding the
- temperature limit will cause damage to the lens and affect the service life of the lens.



| PN | | HK-50@05-90-3030-#0- HK-50@05-60-3030-#0- HK-50@06-30-3030-20- | -1g-12 | Product Name | Product Name HK 12close1-90degree Road lam Lens HK 12close1-60degree Road lam Lens HK 12close1-30degree Road lam Lens | | ns | | |
|------------------|---------|--|--------------------|--------------|--|--------------|------|-----------|--|
| Product material | | PC Custome | | Customer | | | | | |
| Package diagram | | Single Vacuum package Box package | | | | | | | |
| Product packing | | 24 | PC | S/BOX | 4 | BOX/Layer | 15 | Layer/BOX | |
| riodact | packing | 1440 | PC | S/BOX | | | | | |
| | NO. | Material Code | Ite | m name | Specification | ngle box usa | Unit | Remarks | |
| | 1 | 2. 07. 0049 | Plastic | blister box | 23cm*21cm | 60 | PCS | | |
| Packag | 2 | 2. 08. 0001 | Pemembrane | | 25cm*27cm | 60 | PCS | | |
| ing | 3 | 2. 06. 0005 | lnside label paper | | 62mm*42mm | 60 | PCS | | |
| Materi als | 4 | 2. 06. 0005 | BOX la | bel paper | 62mm*70mm | 1 | PCS | | |
| | 5 | 2. 06. 0003 | Large | e baffle | 46cm*42cm | 16 | PCS | | |
| | 6 | 2. 06. 0011 | Са | nrton | 48cm*44cm*37cm | 1 | PCS | | |
| | 7 | | | | | | | | |
| Remarks | | Scattered packaging is not subject to this specification | | | | | | | |
| organization: | | | proofread | ing: | To examine: | Approval: | | | |




Special notice


When gule pass through holes, columns and other structures, or part of the thin structure, will form a weld line. The product which uses multi-point injection welding line will appear because of the combination of sol, as shown below:


Syntheti











Please note:

The appearance of lines in the structure of the product as well as at the screw hole is a normal phenomenon, will not affect the actual use of the product, and can not be avoided at this stage.



Appearance inspection standards

1 Operating procedures 1.1.1Sampling standards, sampling plan and AQL

Test level: GB/T2828.1-2012The first part is according to the acceptance quality limit (AQL) retrieval batch inspection sampling plan, general inspection level II level, CR class defect coefficient 0, MA defect rejection level AQL = 0.65, MI class defect rejection level AQL = 1.0; defect level please see 5.4.

2 Code table

| Code | Code | Unit | Code | Code | Unit |
|------|-------------|------|------|-------------|------|
| | description | | | description | |
| N | Amount/pcs | pcs | D | Diameter | mm |
| L | Length | mm | Н | Depth | mm |
| W | Width | mm | DS | Distance | mm |
| S | Proportion | mm² | SS | Offset | mm |

- 3.1 Sight distance and working hours: Sight distance should be 30-35cm, each side of the inspection time does not exceed 12s,
- 3.1 Sight distance and working holds. Sight distance should be 30-35th, each side of the hispection time does not exceed 12s, the visual angle of 45-135 degrees;

 3.2 Light: 2x40v cool white fluorescent lamp, the light source is 500-550mm away from the lens surface; in order to make the appearance defect can be correctly recognized, the illumination should be 500-1000Lux, and the observation time is 10 seconds.

 3.3 Visual inspection staff should be 1.0 (including corrected visual acuity) above, no color blindness, color weakness.

4 Appearance inspection standards

| Test items | Judging standard | Inspection equipment | Defect level | | |
|------------------|--|----------------------------------|--------------|----|----|
| reschenis | | Testing method | MI | MA | CR |
| | When start the machine and process, all products have to check the appearance of the sample, the appearance of the sample is divided into qualified samples and limited samples. | | | | |
| Check the sample | Qualified sample refers to the appearance and structure standard of the product which recognized by the client, the sample size should be confirmed before mass production; | Sample comparison , visual | | | √ |

| 1 | | 1 | 1 | 1 | |
|---|---|------------------------------------|----------|----------|----------|
| | 2: The limited sample refers to the limit of a particular exceptionally developed sample. Limit the sample only for its specific point of exception to confirm; The priority is higher than the other criteria in | | | | |
| | this table. When there is a limited sample, the limit sample shall prevail. | | | | |
| Raw edge | Not allowed to affect the size and assembly | Visual, point card | | √ | |
| Scratch | Non-optical surface and non-exposed surface scratches should be visually insignificant and the length is less than 1/10 of the maximum surface size. | Visual, point card, calipers | | √ | |
| Fingerprint | Fingerprints are not allowed on all products | Visual | | √ | |
| Foreign objects, black spots, white spots | The product may not be attached to foreign objects, including oil, fiber, dregs of water gap and so on | | | | √ |
| Deformation | Insufficient filling shall not affect the appearance of the assembly and the exposed surfaces. | Visual, feeler | | | √ |
| Poor ejection | Products may not appear bad ejection, including no convex top, thimble printed on the assembly surface shall not be higher than the product surface, non-assembled surface thimble height should not exceed the product size tolerances; thimble printing should be less than the product surface and no more than 0.3; thimble surface treatment should be consistent with the product side. | Visual, point card | | √ | |
| | Ejection strain: the optical surface and the appearance of the exposed surface after assembly are not allowed to have a strain, and the structural surface does not allow visual obvious strain. | | | | |
| Insufficient filling | Insufficient filling shall not affect the appearance of the assembly and the exposed surfaces , The signature sample shall prevail. | Visual, point card | | v | |
| Shrink | When the entire surface of the product shrinks, the optical properties and dimensions must meet the requirements, and the visual will not significantly affect the appearance.Part shrink reference point defects | Visual, point card | | √ | |
| Flow marks、Welding line | 1 : Product does not allow the presence of flow marks and welding lines unless the structure can not be avoided; | Visual | | √ | |
| | 2: The remaining flow marks shall not appear in the optical surface, a single L \leq 10mm, no more than two | | | | |
| Bubble | No bubbles are allowed | Visual | | √ | |
| Foreign objects, black spots, white spots | Not obvious or D ≤ 0.3mm black spots and foreign bodies in the area of 100x100mm not more than 1; Exceeded foreign matter black spots is judged bad. | Visual, point card | √ | | |
| Damaged | No damage is allowed | Visual | | | √ |
| Cold glue | Optical surface may not have cold glue, non- optical surface cold glue should meet the visual is not obvious. | Visual | √ | | |
| | Do not affect the product size, shall not penetrate the optical surface, the cut should be smooth; | | | | |
| Bad incision | 2: Laser cutting products, the optical surface burns shall not occur after the processing is completed. Beading must not affect product installation | Visual | | | √ |
| | 3: Three molds and hot runner gate shall not appear residue. | | | | |
| Scrub | Scrub surface should be uniform, off the scrub phenomenon should not be obvious , A single off scrub imprint requires D \leq 1 mm and no more than 1 area within a 50x50 mm area | Visual | | √ | |
| | aica | | | | |