

Technology Co.,Ltd

Product Approval

Approval number:


Customer:

Product: HK 12in 1-TYPE V street lamp lens

Material Code: 1.02.92172_PC

PN: HK-50@05-135-3030-#0-1g-12_PC

Manufacturer: Chengdu HercuLux Photoelectric Technology Co.,Ltd



	Supplier confirmation				Client confirmation				
Proposed		DATE		Qualified□		5.475			
Project manager		DATE		Unqualified□		DATE			
Audit		DATE		Audit		DATE			
Approved		DATE		Approved		DATE			
Stamp		DATE		Stamp		DATE			

(Confirmation of acceptance by both parties must be signed and sealed)

Factory: Chengdu Shuangliu District, Iot industrial park 2 road HercuLux Photoelectric Park

Phone: 028-85887727 (801) 028-85887990 (801) Fax: 028-85887730 http://www.herculux.com/ Sales Dept: Shenzhen Nanshan District Nanshan Cloud Valley Innovation Industrial Park Comprehensive Service Building,

TEL: 0755-2937 1541 FAX: 0755-2907 5140

*Approval In duplicate, for both supplier and customer.

Disclaimer



Please use this product within the permitted range and environment according to the structure and material of the product. If the usage exceeds the recommended value, please test and verify by yourself. If the product is damaged due to out-of-range use, our company will not be responsible for the warranty.

Product material:

Customized products: The specifications and models of materials used are subject to the agreement between the two parties.

Conventional products: As a product that we continuously research and improve, under the premise of ensuring the quality and availability of the product, our company reserves the right to change the material. If the material specification and model change, without prior notice.

product data:

The measurement data and dimensional tolerances of the 2D drawings in the product data sheet of this acknowledgement are for reference only, and the final size shall prevail in kind.

The measurement data presented in this acknowledgment is a performance test of the product based on our company's internal test conditions and quality requirements, and the reported data is a typical value of the average results of multiple measurements. Therefore, in some cases, the actual product may deviate from the data provided. We reserve the right to notify you in advance of this data.

Product changes and improvements:

Changes and improvements of customized products are subject to the agreement between the two parties in the contract or technical documents.

As the conventional products that we continue to research and improve, our company reserves the right to make technical changes to its products, and reserves the right to make changes to data resulting from improvements without prior notice.

Operation cautions:

- 1. Please wear clean gloves during product assembly to prevent product surface contamination.
- 2. Try to avoid touching the optical surface of the lens when taking the lens.
- 3. When the surface of the product is polluted, please wipe it gently with a soft cotton cloth dipped in analytically pure neutral solvent. It is forbidden to use industrial solvents (alcohol, isopropanol, acetone, ether, toluene, xylene, carbon tetrachloride, MMA monomerm, etc.) wipe.





Basic product information


TEL: 0755-2937 1541 FAX: 0755-2907 5140 http://www.herculux.com/ Date updated: 2023/2/7

Product Picture:							
Size(L*W*H/Φ*H):	L:50mm*W:50mm*H:5.4mm						
Material:	PC						
Effiency:	\						
Temperature(Topr):	Material extreme temperature resistance : -40°C to +120°C long-term use temperature : -40°C to +100°C						
FWHM:	135°						
Matched LES:	3030						
Recommended MAX power:	/						










Technical remark:

- 1. The 3D map is not indicated for rounded corners and draft angle.
- 2. The dimensional tolerances are not specified according to GB/T 14486 2008 MT5.
- 3, The surface has no flash, shrinkage, bubbles and other defects.
- *4. When the lamp adopts rubber ring for waterproofing: the roughness of the contact surface between the radiator and the rubber ring is required: Ra<3.2 μ m

Optical desig						HK-50@05-135-3030-#0-1g-12_P					
ructure desi					1-TYPE V street amp lens		С				
Review	· ·				mber of drawi		qty	wei	ght		
11011211											
Validation			Material:	PC			CDHK				
Vandation											

Tolerance Herance val +0.1 +0.15 +0.2 +0.25 +0.50 +0.80 +1.2 +2.0	MT5	Dii	/2	2~√10	10. 24	24. 65	CF . 140	440. 350	250. 450	> 450	Т	_
	l		√3	3~10	$10^{\sim}24$	24~65	$65^{\sim}140$	$140^{\sim}250$	$250 \sim 450$	<i>></i> 450		
		la di	±0.1	±0.15	±0.2	±0.35	±0.50	±0.80	±1.2	_ <u></u>	٦	








			Standa rd size	Upper Size limit	Lower size limit	Test result 1	Test result 2	Test result 3	Test result 4	Test result 5	Test result 6	Test result 7	Test result 8	Jud gme nt	Remarks	
	OW		50			49. 79	49.8	49. 76	49.8	49.86	49. 9	49. 86	49.8		environment:	
1.Size	S of locatin		45			44. 99	44. 99	44. 99	45	44. 99	45	45	45		In 20 °C -25 °C	
1.5126	D loca	of atin	2			1. 9	1.9	1. 9	1.9	1. 9	1.9	1.9	1. 9		environment to achieve thermal	
	Т	Н	2.15			2. 18	2. 18	2. 26	2. 26	2. 24	2. 22	2. 22	2. 16		equilibrium after the test.	
		Gate shear can not affect the appearance of the lamp														
					See a	ittachm	ent "Ap	pearar	ice Insp	ection	Standa	rds"				
2.Appear	i annaaranc		chment	E		No bu	ırr No		burr	No burr		No burr			- ок	
ce Qualit			_	No		ins	No s	tains	No s	No stains N		o stains				
3.Materia	al			F	PC			Color Tran			nspare	nt		OK		
	estin	sting LE							3030							
4.Optica	Ac	The size and rated power of the light-emitting surface (LES) of the COB recommended by this lens should conform to the parameters in the product basic information table. If it is required to be out of range. According to the heat dissipation capability of the lamp and the actual conditions of the use environment, the lens should be fully tested and tested to prevent the lens life.										f range.				
I index	FW	НМ					Se	e light	distribu	tion cur	ve					
	ang	gle				141	142	141	141.5	141.7	140. 5	142	142. 2			
	fic	ficien				92%	92%	92%	92%	92%	92%	92%	92%			
	acul	See	the sign	ature sa	mple		`									
sive	Comprehen sive judgment								Qualifi	ed				_		

Remarks:

1. Tool Number: V-Vernier Caliper 2D-Quadratic H-Height Gauge M-Tool Microscope P-Needle T-Thick Gauge R-Radius Gauge E-Visual.

2. Ambient temperature on the size of the product refer to the table on



Precautions:

the right

- 1. Please wear clean gloves during the lens assembly process to prevent the lens surface from being contaminated.
- 2. Try to avoid touching the total reflection surface when taking the lens.
- 3. The lens surface is contaminated. Only use a soft cotton cloth dipped in analytically pure neutral solvent to wipe gently. Do not wipe with industrial solvents (alcohol, isopropanol, acetone, ether, toluene, xylene, carbon tetrachloride, MMA Body, etc.).
- 4. The working temperature of the lens should be within the temperature resistance limit of the lens material. Exceeding the temperature resistance limit will cause the lens to crack or melt and affect the service life of the lens. It is recommended that the upper surface temperature of the LED colloid should be less than 120 degrees.



Pl	N	HK-50@05-135-3030-#0-	1g-12_PC	Product Name	HK 12in 1-TYPE V				
Product	material			PC					
Package	diagram	Single Vac	uum package	Box	package	>			
Product	packing	24	A/ Box	4	PCS/Layer				
		14	Layer/Box	1344	A/ Carton				
	NO.	Part No	Part name	Size	Dosage	Unit	Remarks		
	1	2.07.0049	Blister box	23cm*21cm	56	BAG			
Dookogin	2	2.08.0001	PE film	30cm*30cm	56	PCS			
Packagin g	3	2.06.0005	Reel label paper	6.2cm*8cm	56	PCS			
Materials	4	2.06.0005	Box label paper	6.2cm*9.2cm	1	PCS			
	5	2.06.0003	big plate	46.8cm*42.8cm	15	PCS			
	6	2.06.0001	big carton	46.8cm*42.8cm*3 m	^{66c} 1	PCS			
Remarks		packing is not subject to this s thags for each layer and 5 ba			nts shall prevail(The	re are th	nree		




Special notice


When gule pass through holes, columns and other structures, or part of the thin structure, will form a weld line. The product which uses multi-point injection welding line will appear because of the combination of sol, as shown below:


Syntheti











Please note:

The appearance of lines in the structure of the product as well as at the screw hole is a normal phenomenon, will not affect the actual use of the product, and can not be avoided at this stage.



Appearance inspection standards

1 Operating procedures

1.1.1Sampling standards, sampling plan and AQL

Test level: GB/T2828.1-2012The first part is according to the acceptance quality limit (AQL) retrieval batch inspection sampling plan, general inspection level Π level, CR class defect coefficient 0, MA defect rejection level AQL = 0.65, MI class defect rejection level AQL = 1.0; defect level please see 5.4.

2 Code table

Code	Code	Unit	Code	Code	Unit
	description			description	
N	Amount/pcs	pcs	D	Diameter	mm
L	Length	mm	Н	Depth	mm
W	Width	mm	DS	Distance	mm
S	Proportion	mm²	SS	Offset	mm

3 Test conditions

- 3.1 Sight distance and working hours: Sight distance should be 30-35cm, each side of the inspection time does not exceed 12s, the visual angle of 45-135 degrees;
- 3.2 Light: 2x40w cool white fluorescent lamp, the light source is 500-550mm away from the lens surface; in order to make the appearance defect can be correctly recognized, the illumination should be 500-1000Lux, and the observation time is 10 seconds.
 - 3.3 Visual inspection staff should be 1.0 (including corrected visual acuity) above, no color blindness, color weakness.

4 Appearance inspection standards

Test items	ludging standard	Inspection equipment	Defect level		
resciteriis	Judging standard	Testing method	MI	MA	CR
	When start the machine and process, all products have to check the appearance of the sample, the appearance of the sample is divided into qualified samples and limited samples.				
Check the sample	1: Qualified sample refers to the appearance and structure standard of the product which recognized by the client, the sample size should be confirmed before mass production;	Sample comparison , visual			√

1		1	I	İ	
	2: The limited sample refers to the limit of a particular exceptionally developed sample. Limit the sample only for its specific point of exception to confirm; The priority is higher than the other criteria in this table. When there is a limited sample, the limit sample shall prevail.				
Raw edge	Not allowed to affect the size and assembly	Visual, point card		√	
Scratch	1: Non-optical surface and non-exposed surface scratches should be visually insignificant and the length is less than 1/10 of the maximum surface size.	Visual, point card, calipers		√	
Fingerprint	Fingerprints are not allowed on all products	Visual		~	
Foreign objects, black spots, white spots	The product may not be attached to foreign objects, including oil, fiber, dregs of water gap and so on				√
Deformation	Insufficient filling shall not affect the appearance of the assembly and the exposed surfaces.	Visual, feeler			√
Poor ejection	Products may not appear bad ejection, including no convex top, thimble printed on the assembly surface shall not be higher than the product surface, non-assembled surface thimble height should not exceed the product size tolerances; thimble printing should be less than the product surface and no more than 0.3; thimble surface treatment should be consistent with the product side. Ejection strain: the optical surface and the appearance of the exposed surface after assembly are not allowed to have a strain, and the structural surface does not allow	Visual, point card		√	
Insufficient filling	visual obvious strain. Insufficient filling shall not affect the appearance of the assembly and the exposed surfaces, The signature sample shall prevail.	Visual, point card		√	
Shrink	When the entire surface of the product shrinks, the optical properties and dimensions must meet the requirements, and the visual will not significantly affect the appearance.Part shrink reference point defects	Visual, point card		√	
Flow marks、Welding line	1 : Product does not allow the presence of flow marks and welding lines unless the structure can not be avoided;	Visual		√	
	2: The remaining flow marks shall not appear in the optical surface, a single L ≤ 10mm, no more than two				
Bubble	No bubbles are allowed	Visual		>	

Foreign objects, black spots, white spots	Not obvious or D ≤ 0.3mm black spots and foreign bodies in the area of 100x100mm not more than 1; Exceeded foreign matter black spots is judged bad.	Visual, point card	V		
Damaged	No damage is allowed	Visual			√
Cold glue	Optical surface may not have cold glue, non- optical surface cold glue should meet the visual is not obvious.	Visual	V		
	1: Do not affect the product size, shall not penetrate the optical surface, the cut should be smooth;				
Bad incision	2: Laser cutting products, the optical surface burns shall not occur after the processing is completed. Beading must not affect product installation	Visual			√
	3: Three molds and hot runner gate shall not appear residue.				
Scrub	Scrub surface should be uniform, off the scrub phenomenon should not be obvious , A single off scrub imprint requires D \leq 1 mm and no more than 1 area within a 50x50 mm area	Visual		√	