



HERCULUX
恒坤光电

Chengdu HercuLux Photoelectric
Technology Co.,Ltd
Product Approval

Approval number :

Customer :

Product : HK 4in1 45°High-Bay Lens

Material Code : 1.01.23105

PN : HK-50@10-45-5050-20-1g-4

Manufacturer : Chengdu HercuLux Photoelectric Technology Co.,Ltd



Supplier confirmation				Client confirmation			
Proposed		DATE		Qualified <input type="checkbox"/>		DATE	
Project manager		DATE		Unqualified <input type="checkbox"/>		DATE	
Audit		DATE		Audit		DATE	
Approved		DATE		Approved		DATE	
Stamp		DATE		Stamp		DATE	

(Confirmation of acceptance by both parties must be signed and sealed)

Factory: Chengdu Shuangliu District, Iot industrial park 2 road HercuLux Photoelectric Park

Phone : 028-85887727 (801) 028-85887990 (801)

Fax : 028-85887730

<http://www.herculux.cn/>

Sales Dept: Shenzhen Nanshan District Nanshan Cloud Valley Innovation Industrial Park Comprehensive Service Building,

TEL: 0755-2937 1541

FAX: 0755-2907 5140

*Approval In duplicate , for both supplier and customer.



HERCULUX
恒坤光电

Product Approval

TEL: 0755-2937 1541

FAX: 0755-2907 5140

<http://www.herculux.cn/>

Date updated: 2022/6/16

Product Picture:



PN:

HK-50@10-45-5050-20-1g-4

Size(L*W*H/Φ*H):

L:50mm*W:50mm*H:8.4mm

Material:

PC

Efficiency:

\

Temperature(Topr):


Material extreme temperature resistance : -40°C to +120°C
long-term use temperature : -40°C to +100°C

FWHM:

45°

Matched LES:

5050





Technical remark:

1. The 3D map is not indicated for rounded corners and draft angle.
2. The dimensional tolerances are not specified according to GB/T 14486 2008 MT5.
3. The surface has no flash, shrinkage, bubbles and other defects.
- *4. When the lamp adopts rubber ring for waterproofing: the roughness of the contact surface between the radiator and the rubber ring is required: $Ra < 3.2\mu m$

Optical design			HK-50@10-45-5050-20-1g-4	
Structure design			HK 4in1 45°High-Bay Lens	
Review			1.01.23105	
Validation			Material: PC	CDHK

MT5 Tolerance table	Basic size	<3	3~10	10~24	24~65	65~140	140~250	250~450	>450
	olerance val	±0.1	±0.15	±0.2	±0.35	±0.50	±0.80	±1.2	±2.0



Intensity data: (deg , cd) CO-180

A	I	A	I	A	I	A	I	A	I	A	I
-90.0	2.517	-58.5	14.82	-27.0	417.7	4.5	1065	36.0	98.17	67.5	9.661
-88.5	2.882	-57.0	15.90	-25.5	471.7	6.0	1039	37.5	77.33	69.0	9.118
-87.0	3.319	-55.5	17.21	-24.0	526.6	7.5	1004	39.0	62.73	70.5	8.545
-85.5	3.803	-54.0	19.15	-22.5	580.9	9.0	963.0	40.5	53.00	72.0	7.991
-84.0	4.313	-52.5	21.43	-21.0	634.8	10.5	916.8	42.0	46.64	73.5	7.389
-82.5	4.912	-51.0	23.99	-19.5	688.3	12.0	866.0	43.5	40.91	75.0	6.735
-81.0	5.574	-49.5	26.24	-18.0	742.8	13.5	811.5	45.0	33.49	76.5	6.106
-79.5	6.415	-48.0	28.13	-16.5	798.1	15.0	754.7	46.5	28.24	78.0	5.499
-78.0	7.182	-46.5	32.52	-15.0	851.2	16.5	699.2	48.0	24.55	79.5	4.949
-76.5	7.666	-45.0	36.85	-13.5	902.4	18.0	644.7	49.5	21.95	81.0	4.387
-75.0	8.152	-43.5	41.25	-12.0	949.3	19.5	588.5	51.0	19.64	82.5	3.877
-73.5	8.652	-42.0	45.55	-10.5	990.9	21.0	532.6	52.5	17.79	84.0	3.404
-72.0	9.229	-40.5	49.48	-9.0	1027	22.5	477.4	54.0	16.22	85.5	2.990
-70.5	9.798	-39.0	53.46	-7.5	1055	24.0	423.9	55.5	15.07	87.0	2.615
-69.0	10.45	-37.5	57.4	-6.0	1076	25.5	369.6	57.0	14.20	88.5	2.286
-67.5	11.08	-36.0	61.2	-4.5	1091	27.0	313.8	58.5	13.43	90.0	2.075
-66.0	11.66	-34.5	64.8	-3.0	1100	28.5	268.6	60.0	12.81		
-64.5	12.21	-33.0	68.3	-1.5	1105	30.0	227.2	61.5	12.22		
-63.0	12.79	-31.5	71.5	0.0	1104	31.5	189.3	63.0	11.60		
-61.5	13.23	-30.0	74.3	1.5	1097	33.0	155.2	64.5	10.93		
-60.0	13.88	-28.5	76.3	3.0	1084	34.5	124.6	66.0	10.28		

Electricity Parameter:

Current I: 0.1000A Power: 3.450W
Voltage V: 34.50V PF: 1.000


Optical Parameter (Distance=2.459m):

Equivalent Luminous flux: $\Phi_{eff} = 683.7lm$ Efficiency: $Eff = 198.20lm/W$
Diffuse angle: @ (25%): 59.4deg @ (50%): 43.6deg @ (75%): 28.6deg @ (50%): 43.6deg
Diffuse angle: @ (25%): 59.4deg @ (50%): 43.6deg @ (75%): 28.6deg @ (50%): 43.6deg
Imax=1105cd (C=0.0deg,G=-1.0deg) CO-180Plane Imax= 1105cd(G=-1.0deg)
CO-180Plane I0= 1104cd

		Standard size	Upper Size limit	Lower size limit	Test result1	Test result2	Test result3	Test result4	Judgment	Remarks
1.Size	OW	50			50.02	50.17	50.02	50.17		Test environment: In 20 °C -25 °C environment to achieve thermal equilibrium after the test.
	S of locating	45			45.07	45.07	45.07	45.07		
	D of locating	2			1.97	1.95	1.97	1.95		
	TH	2.45			2.6	2.46	2.6	2.46		
	Gate shear can not affect the appearance of the lamp									
See attachment "Appearance Inspection Standards"										
2.Appearance Quality	See attachment "Appearance Inspection Standards"	E	No burr		No burr	No burr	No burr	No burr	OK	
			No stains		No stains	No stains	No stains	No stains		
3.Material	PC				Color	Transparent			OK	
4.Optical index	Testing LED	5050								
	The recommended size and power rating of the LED light source recommended for this lens should be comparable to the source of the test, if it is required to be out of range. According to the heat dissipation capability of the lamp and the actual conditions of the use environment, the lens should be fully tested and tested to prevent the lens life.									
	FWHM	See light distribution curve								
	angle			43.6	43.3	43	43.8			
	Efficiency			90.00%	89.50%	89.00%	89.50%			
Facula	See the signature sample									
Comprehensive judgment	Qualified									


Remarks:

- 1、 Tool Number: V-Vernier Caliper 2D-Quadratic H-Height Gauge M-Tool Microscope P-Needle T-Thick Gauge R-Radius Gauge E-Visual.
- 2、 Ambient temperature on the size of the product refer to the table on the right



Precautions:





1. Please wear clean gloves during the lens assembly process to prevent the lens surface from being contaminated.
2. Try to avoid touching the total reflection surface when taking the lens.
3. The lens surface is contaminated. Only use a soft cotton cloth dipped in analytically pure neutral solvent to wipe gently. Do not wipe with industrial solvents (alcohol, isopropanol, acetone, ether, toluene, xylene, carbon tetrachloride, MMA Body, etc.).
4. The working temperature of the lens should be within the temperature resistance limit of the lens material. Exceeding the temperature resistance limit will cause the lens to crack or melt and affect the service life of the lens. It is recommended that the upper surface temperature of the LED colloid should be less than 120 degrees.

PN	HK-50@10-45-5050-20-1g-4		Product Name	HK 4in1 45°High-Bay Lens			
Product material	PC		Customer				
Package diagram	 <p style="text-align: center;"> Single Vacuum package Box package </p>						
Product packing	12	A/ Box	4	PCS/Layer			
	14	Layer/Box	672	A/ Carton			
Packaging Materials	NO.	Part No	Part name	Size	Dosage	Unit	Remarks
	1	2.07.0049	Blister box	23cm*21cm	56	BAG	
	2	2.08.0001	PE film	30cm*30cm	56	PCS	
	3	2.06.0005	Reel label paper	6.2cm*8cm	56	PCS	
	4	2.06.0005	Box label paper	6.2cm*9.2cm	1	PCS	
	5	2.06.0003	big plate	46.8cm*42.8cm	15	PCS	
	6	2.06.0001	big carton	46.8cm*42.8cm*36cm	1	PCS	
Remarks	The loose packing is not subject to this specification. Customer's requirements shall prevail(There are three layers of 24 bags for each layer and 5 bags for the top layer)						

Special notice

When glue pass through holes, columns and other structures, or part of the thin structure, will form a weld line. The product which uses multi-point injection welding line will appear because of the combination of sol, as shown below:

Syntner



Please note :

The appearance of lines in the structure of the product as well as at the screw hole is a normal phenomenon, will not affect the actual use of the product, and can not be avoided at this stage.

Appearance inspection standards

1 Operating procedures

1.1.1 Sampling standards, sampling plan and AQL

Test level : GB/T2828.1-2012 The first part is according to the acceptance quality limit (AQL) retrieval batch inspection sampling plan, general inspection level II level, CR class defect coefficient 0, MA defect rejection level AQL = 0.65, MI class defect rejection level AQL = 1.0; defect level please see 5.4.

2 Code table

Code	Code description	Unit	Code		Code description	Unit
N	Amount/pcs	pcs	D		Diameter	mm
L	Length	mm	H		Depth	mm
W	Width	mm	DS		Distance	mm
S	Proportion	mm ²	SS		Offset	mm

3 Test conditions

3.1 Sight distance and working hours: Sight distance should be 30-35cm, each side of the inspection time does not exceed 12s, the visual angle of 45-135 degrees;

3.2 Light: 2x40w cool white fluorescent lamp, the light source is 500-550mm away from the lens surface; in order to make the appearance defect can be correctly recognized, the illumination should be 500-1000Lux, and the observation time is 10 seconds.

3.3 Visual inspection staff should be 1.0 (including corrected visual acuity) above, no color blindness, color weakness.

4 Appearance inspection standards

Test items	Judging standard	Inspection equipment	Defect level		
		Testing method	MI	MA	CR
Check the sample	When start the machine and process, all products have to check the appearance of the sample, the appearance of the sample is divided into qualified samples and limited samples.	Sample comparison , visual			
	1: Qualified sample refers to the appearance and structure standard of the product which recognized by the client, the sample size should be confirmed before mass production;				

	2: The limited sample refers to the limit of a particular exceptionally developed sample. Limit the sample only for its specific point of exception to confirm; The priority is higher than the other criteria in this table. When there is a limited sample, the limit sample shall prevail.				
Raw edge	Not allowed to affect the size and assembly	Visual, point card		√	
Scratch	1: Non-optical surface and non-exposed surface scratches should be visually insignificant and the length is less than 1/10 of the maximum surface size.	Visual, point card, calipers		√	
Fingerprint	Fingerprints are not allowed on all products	Visual		√	
Foreign objects, black spots, white spots	The product may not be attached to foreign objects, including oil, fiber, dregs of water gap and so on				√
Deformation	Insufficient filling shall not affect the appearance of the assembly and the exposed surfaces.	Visual, feeler			√
Poor ejection	Products may not appear bad ejection, including no convex top, thimble printed on the assembly surface shall not be higher than the product surface, non-assembled surface thimble height should not exceed the product size tolerances; thimble printing should be less than the product surface and no more than 0.3; thimble surface treatment should be consistent with the product side.	Visual, point card		√	
	Ejection strain: the optical surface and the appearance of the exposed surface after assembly are not allowed to have a strain, and the structural surface does not allow visual obvious strain.				
Insufficient filling	Insufficient filling shall not affect the appearance of the assembly and the exposed surfaces , The signature sample shall prevail.	Visual, point card		√	
Shrink	When the entire surface of the product shrinks, the optical properties and dimensions must meet the requirements, and the visual will not significantly affect the appearance.Part shrink reference point defects	Visual, point card		√	
Flow marks、Welding line	1 : Product does not allow the presence of flow marks and welding lines unless the structure can not be avoided;	Visual		√	
	2: The remaining flow marks shall not appear in the optical surface, a single L ≤ 10mm, no more than two				

Bubble	No bubbles are allowed	Visual		√	
Foreign objects, black spots, white spots	Not obvious or $D \leq 0.3\text{mm}$ black spots and foreign bodies in the area of 100x100mm not more than 1; Exceeded foreign matter black spots is judged bad.	Visual, point card	√		
Damaged	No damage is allowed	Visual			√
Cold glue	Optical surface may not have cold glue, non-optical surface cold glue should meet the visual is not obvious.	Visual	√		
Bad incision	1: Do not affect the product size, shall not penetrate the optical surface, the cut should be smooth;	Visual			√
	2: Laser cutting products, the optical surface burns shall not occur after the processing is completed. Beading must not affect product installation				
	3: Three molds and hot runner gate shall not appear residue.				
Scrub	Scrub surface should be uniform, off the scrub phenomenon should not be obvious , A single off scrub imprint requires $D \leq 1\text{ mm}$ and no more than 1 area within a 50x50 mm area	Visual		√	